

## R42903

U0550

Suggested Use(s)	Folding carton, uncoated paper stock, aqueous coated paper stock.
Equipment Application	Non-contact extrusion
Typical Properties	
Viscosity	300-350
Wt Solids (%)	48-52
pH	4.0-6.0
Bulk Density	8.7-9.1 lb/gal
Appearance	white, colored or UV fluorescing liquid
Shelf Life	6 months from date of sale
Characteristics	<p>Specially formulated for gluing aqueous coatings to paper stock.</p> <p>Formulated for increase penetration on difficult to bond paper stock.</p> <p>Provides good machining characteristics with fast set and moderate open time.</p> <p>Meets compositional requirements of <u>21CFR175.105</u> for adhesives intended for incidental food contact applications.</p>
Storage and Handling	<p>Agitate thoroughly before use.</p> <p>Do not store directly on concrete floor.</p> <p>Storage temperature 60-90F</p> <p>Keep containers covered to prevent skinning and contamination.</p> <p>Protect from freezing.</p> <p>Clean dried film with water/acetone mixture.</p> <p>Clean wet film with warm water.</p> <p>Do not mix with other adhesives.</p>

The information contained herein is based on tests and reports considered to be reliable but is presented without guarantee or responsibility as to the applicability of correctness of this information or the suitability of our products whether used singly or in combination with other products. The product referred to above is sold without warranty, express or implied.

TBR42903 - rev 1 - 7.16.2009