

L179

WD 1000

Suggested Use(s)	Self-seal and fugitive application.
Equipment Application	Wheel, spray, or extrusion.
Typical Properties	
Viscosity	100-350 cps
Wt Solids (%)	58-62
pH	11.0
Bulk Density	7.7-8.1 lbs/gal
Appearance	white or colored liquid
Shelf Life	3 months from date of sale
Characteristics	Dried film is peelable. Commonly referred to as “booger” glue. Dried glue film can be used as co-adhesive on envelopes when folded dry onto itself. Excellent aging and machining latex. Specially formulated for peelable applications such as mailers, inserts and outserts. Not compatible with other adhesives, copper, or brass. Meets compositional requirements of 21CFR175.105 for adhesives intended for incidental food contact applications.
Storage and Handling	Agitate thoroughly before use. Do not store directly on concrete floor. Storage temperature 60-90F Keep containers covered to prevent skinning and contamination. Protect from freezing. Do not mix with other adhesives. Slight ammonia odor, do not inhale. Clean up with 9.5-10.5 Ph water of low household concentrate of ammonia, 10-15% in water. Condition application equipment when switching between latex and other types of cold adhesives.

The information contained herein is based on tests and reports considered to be reliable but is presented without guarantee or responsibility as to the applicability of correctness of this information or the suitability of our products whether used singly or in combination with other products. The product referred to above is sold without warranty, express or implied.

TBL179 – rev 6 – 6.12.2009